



CEWELD MA 300

TYPE	300 HB GMAW welding wire for rebuilding and bufferlayers						
ANWENDUNGEN	Rebuilding machine parts before Hardfacing and cladding crane and or train wheels to achieve a wear resistant layer against high pressure caused by metal to metal friction						
EIGENSCHAFTEN	CEWELD MA 300 offers almost full hardness in the first layer and can be applied without any risk of cracking. Multiple layers or sandwich layers are possible before Hardfacing and will help to increase the hardness (wear resistance) from the hardface layer.						
KLASSIFIKATION	AWS	A 5.21: ERF _e -1					
	EN ISO	14700: S Fe1					
	DIN	8555: MSG-5-GZ-300					
	W.Nr.	~1.7339					
	F-nr	71					
GEEIGNET FÜR	300 HB hardfacing alloy, sprocket wheels, rebuilding, crushing hammers, Rebuilding machine parts before hardfacing and cladding crane and or train wheels to achieve a wear resistant layer against high pressure caused by metal to metal friction.						
ZULASSUNGEN	CE						
SCHWEISSPOSITIONEN	      						
TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)	C	Si	Mn	Cr	Ni	Mo	Ti
	0.1	0.6	1.1	1.3	0.05	0.5	0.003
MECHANISCHE GÜTEWERTE							
RÜCKTROCKNUNG	Not required						
GAS ACC. EN ISO 14175	M21						