

CEWELD AlMg 4.5Mn

TYPE

Mig aluminium welding wire with high corrosion resistance

ANWENDUNGEN

Filler metal for Magnesium and Manganese alloyed Aluminium with a maximum Magnesium content of 5%. This alloy shows very good mechanical properties that make it ideal for applications in shipyards, in car and railway industry and constructions of reservoirs and tanks.

EIGENSCHAFTEN

Excellent weldability and good mechanical strength combined with good corrosion resistance against seawater are typical for this alloy. The weld deposit is free from porosity due to the special shaving process and cleaning method during production. AlMg4,5Mn is one of the highest grades within the range of aluminum alloys and covers a weight range of alloys. Thicker sections should be preheated (150°C) prior to welding. Qualified by Lloyds for manual and (semi)automatic welding.

KLASSIFIKATION

AWS

A 5.10: ER5183

EN ISO

18273: S Al 5183 (AlMg4,5Mn0,7(A))

W.Nr.

3.3548

F-nr

22

GEEIGNET FÜR

Aluminium alloys:

AlMg4,5Mn, AlMg5, AlMg2Mn0,8, AlZnMg1, AlZnMgCu0,5, AlMgSi0,5, AlMgSi1,AlMgSi0,5, G-AlMg10, G-AlMg5, G-AlMg3Si, G-AlMg5Si,

3.2315, 3.3545, 3.3547, 3.3535, 3.3555, 3.3206, 3.3210, 3.2315, 3.3211, 3.4335,

EN AW 5086, EN AW 5083, EN AW 5019, EN AW 5019, EN AW 6060, EN AW 6005A, EN AW 6082, EN AW 6061,

EN AW 7020, EN AC 51300, EN AC 51400,EN AW-6082

ZULASSUNGEN

CE, Lloyds: MATS/NTH-1043/7/1

SCHWEISSPOSITIONEN















TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)

Mn	Cr	Ti	Al	Mg
0.7	0.1	0.15	Rem.	4.5

MECHANISCHE GÜTEWERTE


Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded	140	300	18	30	HRc

RÜCKTROCKNUNG

Not required

GAS ACC. EN ISO 14175

I1, I3



CEWELD AlMg 4.5Mn

ALMG 4.5MN 0,8MM

Packaging	KG/unit	EanCode
BS-300	7	8720663406996
D-100	0,50	8720663407009
D-200	2	8720663407016

ALMG 4.5MN 1,0MM

Packaging	KG/unit	EanCode
BS-300	7	8720663407023
D-100	0,50	8720663407030
D-200	2	8720663407047

ALMG 4.5MN 1,2MM

Packaging	KG/unit	EanCode
BS-300	7	8720663407061

ALMG 4.5MN 1,6MM

Packaging	KG/unit	EanCode
BS-300	7	8720663407078

ALMG 4.5MN 2,4MM

Packaging	KG/unit	EanCode
BS-300	7	8720663407085