



CEWELD OA 63

TYPE	High-alloyed tubular wire on a C-Cr-Nb-B carbide basis for extreme hard deposits on parts subject to strong mineral abrasion.		
ANWENDUNGEN	Rebuilding and or protecting wear parts that faces extreme abrasion and medium to low impact.		
EIGENSCHAFTEN	Extreme wear resistance even at higher temperatures. The deposit gives already a High hardness in the first layer. A buffer layer is recommended in case of sensible base material or old layers. Weldable without protective gas		
KLASSIFIKATION	EN ISO	14700: T Fe15	
	DIN	8555: MF 10-GF-65-G	
GEEIGNET FÜR	63-67 HRC hardfacing alloy ,Fan blades, Bucket lips, Mining, Cement, Mineral hammers, coke wear plates etc.		

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)

C	Si	Mn	Cr	Nb	B
4.7	1.7	0.2	22	7	1

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				63 HRc

RÜCKTROCKNUNG 140°C / 24 hr

GAS ACC. EN ISO 14175



CEWELD OA 63

OA 63 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403728

OA 63 2,4MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403735