



CEWELD L-Ag30Sn

TYPE High silver containing cadmium free brazing alloy

ANWENDUNGEN Brazing a weight range of different metals in maintenance and repair with excellent strength, Boiler making, tubing, cooling equipment etc.

EIGENSCHAFTEN The presence of tin improves the fluidity is useful to increase the activity of the flux. Do not use this alloy above working temperatures of 200 °C.
Flux/Paste: CEWELD Super-Flux

KLASSIFIKATION EN ISO 17672: Ag 130

GEEIGNET FÜR Brazing: Steels, Copper, Copper alloys, Stainless steel, Nickel and Nickel alloys. Also suitable for dissimilar joints between these metals.

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)

Cu	Zn	Sn	Ag
36	32	2	30

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		460		HRc

RÜCKTROCKNUNG Not required

MELTING RANGE 665 - 755°C

GAS ACC. EN ISO 14175