



CEWELD AA 4820

TYPE	High-alloyed tubular wire for head resistant Steel. (Typ 25 4, 1.4820),					
APPLICATIONS	CEWELD AA 4820 is for welding cap layers for joining refractory Cr-Al-Si steels. Cladding corrosion resistant overlays. Cladding heat resistant overlays up to 1100°C. Cladding components in a sulphurous environment.					
PROPERTIES	Higher productivity, higher deposition rates and improved wetting properties compared to solid wires with comparable analysis. Excellent weld metal quality and X-ray soundness. When welding, care should be taken to minimize the heat input, because materials of this composition have a tendency to embrittle in the temperature range of approx. 600-800° C. The interpass temperature should not exceed 300° C. Therefore, the interpass temperature should not exceed 300°C.					
CLASSIFICATION	EN ISO	17633-A: TZ 25 4 M M21 1				
	W.Nr.	1.4820				
	FM	5				
SUITABLE FOR	1.4710, 1.4712, 1.4713 , 1.4722, 1.4724 , 1.4729, 1.4740, 1.4742 , 1.4745, 1.4762 , 1.4773, 1.4776, 1.4820, 1.4821 , 1.4822, 1.4823 G-X30CrSi6, G-X40CrSi23 TP433, X10CrSi6 502, X10CrAl24 TP443, X10CrAl7 502, X8Cr30, X10CrSi13, G-X40CrSi29, X10CrAl13 TP405-CA15, G-X12CrSi 26 5, G-X40CrSi13, X20CrNiSi 25 4 TP329, G-X40CrSi17, G-X40CrNi 25 4 TP329, X10CrAl18 430B-TP430, G-X40CrNiSi 27 4 TP329HC AISI 327, ASTM A297HC					
APPROVALS						
WELDING POSITIONS	 PA  PB  PC  PD  PE  PF					
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Ni	Mo
	0.08	1	0.7	25	4.6	0.25
MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	
	As Welded	>450	>650	>15	94 HB	
REDRYING	Not required					
GAS ACC. EN ISO 14175	M21					



CEWELD AA 4820

AA 4820 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415875
Drum	250	8720663415882