



CEWELD AA 904L

TYPE	Rutile fluxcored austenitic filler metal with excellent corrosion resistance									
APPLICATIONS	Tanks and process vessels, piping systems, agitators, rotors, cast pumps and valves for use in fertilizer, phosphoric-, sulphuric-, acetic- and acid environments.									
PROPERTIES	The Ceweld AA 904L is used for welding materials of similar chemical composition which are used for fabrication of equipment and vessels for handling of sulfuric acid and many chloride containing media. This fluxcored wire may also find applications for joining Type 317L material where improved corrosion resistance in specific media is needed. In order to reduce the propensity for fissuring and hot cracking, the low melting constituents such as carbon, silicon, and phosphorus are controlled to lower levels in this alloy. Suitable only in down-hand positions.									
CLASSIFICATION	AWS	A 5.22: ~385T0-4								
	EN ISO	17633-A: T Z 20 25 5 Cu N L R M21 3								
	W.Nr.	1.4539								
	F-nr	5								
	FM	6								
SUITABLE FOR	1.4539 / 904L CrNiMoCu / 20 25 5 Cu L 1.4465, 1.4500, 1.4505, 1.4506, 1.4519, 1.4531, 1.4536, 1.4537, 1.4538, 1.4539, 1.4573, 1.4585, 1.4586 X1CrNiMoN25-25-2, X1NiCrMoCu 25-20-5, X1CrNiMoCuN 25-25-5, X2NiCrMoCuN25-20-5, X2NiCrMoCuN20-18, X4NiCrMoCuNb 20-18-2, X5NiCrMoCuTi20-18, X5NiCrMoCuNb22-18 ASTM A182, UNS N08904, S31726 Uranus B6, AISI 904L, Z2NCDU25-20,									
APPROVALS	CE									
WELDING POSITIONS	 PA  PB									
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu
	0.035	0.5	3.5	0.02	0.002	20	25.5	4.5	0.072	1.6
MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V				Hardness	
					-196°C					
	As Welded	430	640	32	35				HRc	
REDRYING	Not required									
GAS ACC. EN ISO 14175	M21									



CEWELD AA 904L

AA 904L 1.2MM

Packaging	KG/unit	EanCode
BS-300	15	8720682050279