



CEWELD MA 500

TYPE	Solid welding wire for rebuilding and hardfacing.				
APPLICATIONS	Rebuilding parts that are subject to abrasion combined with heavy impact.				
PROPRIÉTÉS	Weld deposit with high carbon content offering excellent weldability.				
CLASSIFICATION	EN ISO W.Nr.	14700: S Fe2 1.8425			
CONVIENT POUR	Crushers, bucket teeth, hammers, crushers, pressure blocks etc.				
AGRÉMENTS	CE				
POSITIONS DE SOUDAGE	 PA  PB  PC  PD  PE  PF				
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C 1.1	Si 0.4	Mn 1.9	Cr 1.8	Al 0.1
PROPRIÉTÉS MÉCANIQUES	Heat Treatment As Welded		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)
ETUVAGE	Not required				
GAS ACC. EN ISO 14175	M21				



CEWELD MA 500

MA 500 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403087